

Braskem PP H375-04

Polypropylene Homopolymer

Braskem America Inc.

Message:

Consistent processability, good color stability, low water carryover, high speed processing

Applications

Suggested uses include nonwoven applications

General Information			
Features	Workability, good		
	Fast molding cycle		
	Good color stability		
	Low water portability		
Uses	Non-woven fabric		
Agency Ratings	FDA 21 CFR 177.1520		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	34.6	MPa	ASTM D638
Tensile Elongation ² (Yield)	8.7	%	ASTM D638
Flexural Modulus - 1% Secant ³	1310	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	32	J/m	ASTM D256A
NOTE			
1.	51 mm/min		
2.	51 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT