

Supol HT960E Black

Polypropylene Homopolymer

LyondellBasell Industries

Message:

30% mineral filled Polypropylene. High stiffness.

General Information			
Filler / Reinforcement	Mineral,30% Filler by Weight		
Features	High Stiffness		
	Homopolymer		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	2800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	3.0	kJ/m ²	ISO 180/1A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT