

SCHULAFORM® 9 A GF 10

Acetal (POM) Copolymer

A. Schulman Europe

Message:

10% glass fibre reinforced POM

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.47	g/cm³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	7.00	cm³/10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	179	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4500	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	70.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	4.0	%	ISO 527-2/1A/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	47	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	144	°C	ISO 75-2/Af
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Burning Rate (2.00 mm)	34	mm/min	ISO 3795
Flammability Classification			IEC 60695-11-10, -20
1.50 mm	HB		
3.00 mm	HB		
Glow Wire Flammability Index			IEC 60695-2-12
--	625	°C	
3.00 mm	625	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
--	650	°C	
3.00 mm	650	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

