

LNP™ STAT-KON™ EX11318C compound

Polyether Imide

SABIC Innovative Plastics Asia Pacific

Message:

LNP STAT-KON EX11318C is a polyetherimide compound reinforced with carbon fiber for good stiffness, dimension stability and has extremely high level of cleanliness for the most demanding application. A unique feature of this material is its low C18-C40 hydrocarbons. This compound is manufactured using LNP CCS Technology.

General Information			
UL YellowCard	E207780-101260584		
Filler / Reinforcement	Carbon Fiber		
Features	Good Dimensional Stability		
	Good Stiffness		
	Low (to None) Ion Content		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.10 to 0.20	%	
Across Flow : 24 hr	0.15 to 0.25	%	
Water Absorption (24 hr, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	21800	MPa	ASTM D638
Tensile Strength ² (Break)	211	MPa	ASTM D638
Tensile Elongation ³ (Break)	1.9	%	ASTM D638
Flexural Modulus ⁴ (50.0 mm Span)	18100	MPa	ASTM D790
Flexural Strength ⁵ (Break, 50.0 mm Span)	270	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	48	J/m	ASTM D256
Unnotched Izod Impact (23°C)	380	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	203	°C	ASTM D648
CLTE			ASTM E831
Flow : -40 to 40°C	4.6E-6	cm/cm/°C	
Transverse : -40 to 40°C	4.3E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+3 to 5.0E+5	ohms	ASTM D257
Volume Resistivity	5.0E+3 to 5.0E+6	ohms · cm	ASTM D257
Static Decay ⁶	0.1	sec	FTMS 101B

Injection	Nominal Value	Unit
Drying Temperature	150	°C
Drying Time	4.0 to 6.0	hr
Drying Time, Maximum	24	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 to 60	%
Rear Temperature	330 to 380	°C
Middle Temperature	340 to 380	°C
Front Temperature	345 to 380	°C
Nozzle Temperature	345 to 380	°C
Processing (Melt) Temp	350 to 380	°C
Mold Temperature	135 to 165	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm
Vent Depth	0.025 to 0.076	mm

NOTE

1. 50 mm/min
2. Type I, 5.0 mm/min
3. Type I, 5.0 mm/min
4. 1.3 mm/min
5. 1.3 mm/min
6. 5000V to <50V

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT