

Huaфон JF-W-D6055A

Polyurethane
Huaфон Group Co., Ltd.

Message:

Impregnation Resin with Hydrolysis Resistance
Characteristics
Mid soft type, 24 hours hydrolysis resistance, yellowing resistance, NOx resistance, uniform film-forming structure, good elasticity, good anti-sticking.
Applications
For high density technics impregnation

| General Information | | |
|-------------------------------|---------------------------|------|
| Features | High Elasticity | |
| | Hydrolysis Resistant | |
| | Non-Stick | |
| | Soft | |
| Uses | Impregnation Applications | |
| Additional Information | Nominal Value | Unit |
| Solvents | DMF | |
| Uncured Properties | Nominal Value | Unit |
| Solids Content | 34 to 36 | % |
| Viscosity (25°C) | 100 to 160 | Pa·s |
| Cured Properties | Nominal Value | Unit |
| Tensile Modulus (100% Secant) | 4.50 to 5.50 | MPa |
| Tensile Strength | > 35.0 | MPa |
| Tensile Elongation at Break | > 350 | % |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT