

MAJ'ECO DEN060LA

Biodegradable Polymers

AD majoris

Message:

MAJ'ECO DEN060LA is a bio polymer material intended for injection moulding.
MAJ'ECO DEN060LA has been developed especially for demanding applications in various engineering sectors.

APPLICATIONS

Product such as:

- Boxes
- Racks
- Technical components

General Information			
Features	Recyclable Material		
	Renewable Resource Content		
Uses	Racks		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.25	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	12	g/10 min	ISO 1133
Molding Shrinkage	5.0E-3	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	55.0	MPa	ISO 527-2
Tensile Strain (Break)	5.2	%	ISO 527-2
Flexural Modulus	2550	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	25	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	150	°C	ISO 3146
Injection	Nominal Value	Unit	
Drying Temperature	55.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	170 to 200	°C	
Mold Temperature	20.0 to 40.0	°C	
Screw Speed	100	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT