

Rynite® RE5264 NC010

THERMOPLASTIC POLYESTER RESIN

DuPont Performance Polymers

Message:

36% Glass Reinforced Polyethylene Terephthalate

General Information	
Filler / Reinforcement	Glass Fiber,36% Filler by Weight
Additive	Mold Release
Forms	Pellets
Processing Method	Injection Molding
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)
	Secant Modulus vs. Strain (ISO 11403-1)
	Shear Modulus vs. Temperature (ISO 11403-1)

Physical	Nominal Value	Unit	Test Method
Density	1.64	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (280°C/5.0 kg)	16.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.80	%	
Flow	0.30	%	

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	14000	MPa	ISO 527-2
Tensile Stress (Break)	207	MPa	ISO 527-2
Tensile Strain (Break)	2.4	%	ISO 527-2

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	65	kJ/m ²	ISO 179/1eU

Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	246	°C	ISO 11357-3

Electrical	Nominal Value	Unit	Test Method
Electric Strength	22	kV/mm	IEC 60243-1

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

