Idemitsu PS NS-050

High Impact Polystyrene

Idemitsu PS

Message:

Idemitsu PS NS-050 is a high impact polystyrene product. It can be processed by extrusion or injection molding and is available in the Asia-Pacific region. Typical application areas are: housing. Features include: flame retardant/rated flame Flame Retardant beautiful

| General Information | |
|---------------------|----------------------|
| Additive | Flame retardancy |
| Features | Excellent appearance |
| | Flame retardancy |
| | |
| Uses | Shell |
| UL File Number | E63304 |
| Forms | Particle |
| Processing Method | Extrusion |
| | Injection molding |

| Physical | Nominal Value | Unit | Test Method |
|---|---------------|----------|-------------|
| Specific Gravity | 1.15 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (200°C/5.0 kg) | 7.0 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 23.5 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 40 | % | ASTM D638 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 69 | J/m | ASTM D256 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating (2.00 mm) | V-0 | | UL 94 |
| Additional Information | | | |
| Heat Distortion Temperature, ASTM D648: 7 | 8°C | | |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 70.0 | °C | |
| Drying Time | 1.0 - 2.0 | hr | |
| Rear Temperature | 180 - 210 | °C | |
| Middle Temperature | 190 - 220 | °C | |
| Front Temperature | 210 - 240 | °C | |
| Nozzle Temperature | 200 - 230 | °C | |
| Mold Temperature | 40.0 - 60.0 | °C | |

| Extrusion | Nominal Value | Unit | |
|-----------------------|---------------|------|--|
| Drying Temperature | 70.0 | °C | |
| Drying Time | 1.0 - 2.0 | hr | |
| Cylinder Zone 1 Temp. | 160 - 200 | °C | |
| Cylinder Zone 2 Temp. | 180 - 220 | °C | |
| Cylinder Zone 3 Temp. | 200 - 240 | °C | |
| Cylinder Zone 4 Temp. | 200 - 240 | °C | |
| Die Temperature | 190 - 220 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

