

# PolyBlend™ 1100 75A

Polyurethane

CardioTech International, Inc.

## Message:

PolyBlend™ 1100 75A is a polyurethane material. This product is available in North America and is processed by extrusion or injection molding.

PolyBlend™ The main features of 1100 75A are:

high strength

plasticization

General Information			
Additive	Plasticizer		
Features	Aroma		
	High tensile strength		
	Good stripping		
	Good melt strength		
	Soft		
	Extended tensile rate		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Hardness			
Nominal Value			Test Method
Durometer Hardness (Shore A)	75		ASTM D2240
Elastomers			
Nominal Value	Unit	Test Method	
Tensile Stress			ASTM D412
100% strain	2.90	MPa	ASTM D412
300% strain	5.03	MPa	ASTM D412
Tensile Strength (Yield)	22.4	MPa	ASTM D412
Tensile Elongation (Yield)	580	%	ASTM D412
Tear Strength <sup>1</sup>	42.0	kN/m	ASTM D624
Additional Information			
Tensile Modulus, ASTM D412-61T: 400 psi			
Extrusion			
Nominal Value			Unit
Cylinder Zone 1 Temp.	202		°C
Cylinder Zone 2 Temp.	207		°C
Cylinder Zone 3 Temp.	213		°C
Melt Temperature	213		°C
Die Temperature	210		°C
Extrusion instructions			

---

Clamp Temperature: 415 °FL/D Screw Ratio: 24:1

---

NOTE

---

1. C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

