

HIPLEX® TR 130

High Density Polyethylene

HIP-PetroHemija

Message:

HIPLEX® TR-130, copolymer of ethylene and hexene is tailored for blown film production. Extraordinary melt toughness made possible to get film down to 0.006 mm thickness. Extruded film has high impact resistance, good tear strength, excellent antiblock and good barrier properties, low gel content and excellent sealing and printing properties.

Applications:

HIPLEX® TR-130 is suitable for production of advertising bags, industrial bags, bags for food package, and for production of composite films and blends with other kind of polyethylene.

HIPLEX® TR-130 has Health Certificate issued by Institute for Health Protection of Serbia. Also, HIPLEX® TR-130 has Statement of Conformity, which declares product's conformity with the European norms for materials intended to come into contact with foodstuffs. Statement of Conformity is issued by Institute for Public Health, Maribor, Slovenia.

General Information			
Additive	Antiblock		
Features	Antiblocking		
	Barrier Resin		
	Copolymer		
	Excellent Printability		
	Food Contact Acceptable		
	Good Heat Seal		
	Good Melt Strength		
	Good Tear Strength		
	Hexene Comonomer		
	High Impact Resistance		
	Low Gel		
Uses	Bags		
	Blending		
	Film		
	Food Packaging		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Pellets		
Processing Method	Blown Film		
	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.940	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.18	g/10 min	ISO 1133

Environmental Stress-Cracking Resistance (F50)	> 1000	hr	ASTM D1693B
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	58		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	18.0	MPa	
Break	32.0	MPa	
Tensile Strain (Break)	900	%	ISO 527-2
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	μm	
Tensile Stress			ISO 527-3
MD : Yield, 25 μm	24.0	MPa	
TD : Yield, 25 μm	19.0	MPa	
MD : Break, 25 μm	43.0	MPa	
TD : Break, 25 μm	33.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break, 25 μm	550	%	
TD : Break, 25 μm	700	%	
Dart Drop Impact (25 μm)	88	g	ASTM D1709
Elmendorf Tear Strength ¹			ASTM D1922
MD : 25.0 μm	42.5	kN/m	
TD : 25.0 μm	251.0	kN/m	
Blow Molding Temperature ²	195 to 220	°C	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	120	°C	ISO 306
NOTE			
1.	Blown Film		
2.	Blow-up ratio: 3.5-5 : 1, Neck height: 6-10 times die diameter		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT