

KOCETAL® UR303

Acetal (POM) Copolymer

Kolon Plastics, Inc.

Message:

KOCETAL® UR303 is an Acetal (POM) Copolymer product. It is available in Asia Pacific, Europe, Latin America, or North America. Applications of KOCETAL® UR303 include automotive, electrical/electronic applications and engineering/industrial parts.

Characteristics include:

Flame Rated

Impact Modified

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
Uses	Fasteners		
	Switches		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.7	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.25	%	ASTM D570

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	65		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	47.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	100	%	ASTM D638
Flexural Modulus (23°C)	1880	MPa	ASTM D790
Flexural Strength (23°C)	68.0	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648A
0.45 MPa, Unannealed	148	°C	
1.8 MPa, Unannealed	86.0	°C	
Melting Temperature	166	°C	ASTM D1525
CLTE - Flow	1.3E-5	cm/cm/°C	ASTM D696

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149

Dielectric Constant	3.70		ASTM D150
Dissipation Factor (1 MHz)	6.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

