

OTECH PVC OW135 - Riser Insulation

Polyvinyl Chloride

OTECH Corporation

Message:

RISER INSULATION COMPOUNDS

Applications

THHN, THWN, THWN-2, MTW,

60°C OIL, SUNLIGHT 720 HR.

| General Information | | |
|-----------------------------|---------------------------|-------------------|
| Uses | Insulation | |
| | Wire & Cable Applications | |
| Physical | Nominal Value | Unit |
| Specific Gravity | 1.35 | g/cm ³ |
| Hardness | Nominal Value | Unit |
| Durometer Hardness (10 sec) | 93 | |
| Mechanical | Nominal Value | Unit |
| Tensile Strength | 17.9 | MPa |
| Tensile Elongation (Break) | 220 | % |
| Additional Information | Nominal Value | Unit |
| Limited Oxygen Index | 29 | % |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

