

# Sumikon® PM-9630 (Type: JT Black)

Phenolic

SBHPP

## Message:

SUMIKON® PM-9630 (Type JT Black) is Glass fiber and Inorganic filler filled resol resin (non-ammonia phenolic) molding compound with good electronic property and heat resistance. This grade is official registered UL with V-0 (t=0.16).

General Information	
Filler / Reinforcement	Glass fiber reinforced material Inorganic filler
Features	Good electrical performance Heat resistance, medium
RoHS Compliance	RoHS compliance
Appearance	Black
Processing Method	Resin transfer molding Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.77	g/cm <sup>3</sup>	JIS K6911
Molding Shrinkage - Flow	0.16	%	JIS K6911
Water Absorption (Equilibrium)	0.090	%	JIS K6911
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	137	MPa	JIS K6911
Flexural Modulus	14600	MPa	JIS K6911
Flexural Strength	208	MPa	JIS K6911
Compressive Strength	208	MPa	JIS K6911
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.4	kJ/m <sup>2</sup>	JIS K6911
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	300	°C	JIS K6911
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength <sup>1</sup>	9.0	kV/mm	JIS K6911
Arc Resistance	179	sec	JIS K6911
Insulation Resistance			JIS K6911
-- <sup>2</sup>	4.0E+12	ohms	JIS K6911
-- <sup>3</sup>	1.0E+12	ohms	JIS K6911
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.160 mm)	V-0		UL 94

## NOTE

- |    |                         |
|----|-------------------------|
| 1. | Method B (step by step) |
| 2. | As molded               |
| 3. | After boiling           |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

