

ENGAGE™ 8207

Polyolefin Elastomer

The Dow Chemical Company

Message:

ENGAGE™8207 polyolefin elastomer is an ethylene-octene copolymer with excellent flow properties and has a wide range of applications in general-purpose thermoplastic elastomers.

after blending with polypropylene (PP) and polyethylene (PE), ENGAGE 8207 has particularly excellent impact resistance and is especially suitable for processing and application fields requiring slightly higher melt flow rate. ENGAGE 8207 has high filler addition and excellent electrical properties (after crosslinking). The product has excellent thermal aging properties, compression deformation and weather resistance.

Main features:

pellets

Excellent flow characteristics

high filler addition

Excellent electrical performance

The impact resistance of polypropylene and polyethylene can be improved after addition

Excellent thermal aging performance, compression deformation and weather resistance after curing

Added talcum powder (untreated, 1 µm)

Application field:

general purpose thermoplastic elastomer

Impact modification

Wires and cables

General Information			
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.870	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Mooney Viscosity (ML 1+4, 121°C)	8	MU	ASTM D1646
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 second, molded	66		ASTM D2240
Shore D, 1 second, molded	17		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant ¹ (Compression Molded)	2.30	MPa	ASTM D638
Tensile Strength ² (Break, Compression Molded)	5.70	MPa	ASTM D638
Tensile Elongation ³ (Break, Compression Molded)	1100	%	ASTM D638
Flexural Modulus			ASTM D790
1% secant: Molding	10.9	MPa	ASTM D790
2% secant: Molding	10.8	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ⁴	37.1	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-53.0	°C	Internal method

Vicat Softening Temperature	37.0	°C	ASTM D1525
Melting Temperature (DSC) ⁵	59.0	°C	Internal method
Peak Crystallization Temperature (DSC)	44.0	°C	Internal method

Additional Information

对无滑石粉产品测量的属性.

NOTE

1.	510 mm/min
2.	510 mm/min
3.	510 mm/min
4.	C mould
5.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

