

LNP™ VERTON™ UV00ASU compound

Polyphthalamide

SABIC Innovative Plastics

Message:

LNP VERTON UV00ASU is a compound based on Polyphthalamide resin containing 50% Long Glass Fiber. Added features of this material include: UV Stabilized, Heat Stabilized, Structural.

Also known as: LNP* VERTON* Compound UF-700-10 HS UV

Product reorder name: UV00ASU

General Information			
Filler / Reinforcement	Long Glass Fiber,50% Filler by Weight		
Additive	Heat Stabilizer		
	UV Stabilizer		
Features	Heat Stabilized		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density			
--	1.66	g/cm ³	ISO 1183
--	1.67	g/cm ³	ASTM D792
Molding Shrinkage			
Flow : 24 hr	0.20	%	ASTM D955, ISO 294-4
Across Flow : 24 hr	0.50	%	ASTM D955
Across Flow : 24 hr	0.48	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	19300	MPa	ASTM D638
--	19200	MPa	ISO 527-2/1
Tensile Strength			
Yield	258	MPa	ASTM D638
Yield	222	MPa	ISO 527-2
Break	258	MPa	ASTM D638
Break	222	MPa	ISO 527-2
Tensile Elongation			
Yield	1.8	%	ASTM D638
Yield	1.4	%	ISO 527-2
Break	1.8	%	ASTM D638
Break	1.4	%	ISO 527-2
Flexural Modulus			
--	17200	MPa	ASTM D790

--	17000	MPa	ISO 178
Flexural Strength			
--	386	MPa	ASTM D790
--	393	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	270	J/m	ASTM D256
23°C ²	42	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1200	J/m	ASTM D4812
23°C ³	78	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	9.90	J	ASTM D3763
--	7.20	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	291	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	296	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	266	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	272	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	3.1E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Transverse : -40 to 40°C	1.4E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	1.5E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15	%	
Rear Temperature	316 to 327	°C	
Middle Temperature	321 to 332	°C	
Front Temperature	332 to 343	°C	
Processing (Melt) Temp	316 to 332	°C	
Mold Temperature	138 to 166	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

