

AKROMID® B3 GF 30 9 RM-M black (3099)

Polyamide 6
AKRO-PLASTIC GmbH

Message:

AKROMID® B3 GF 30 9 RM-M black (3099) is a 30% glass fibre reinforced and process improved polyamide 6 with high stiffness and strength and limited moisture absorption
Applications are housings and other dimensional stable parts in the automotive and electronic industry

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Features		Good Dimensional Stability		
		High Stiffness		
		High Strength		
		Low Moisture Absorption		
Uses		Automotive Applications		
		Electrical/Electronic Applications		
		Housings		
Appearance		Black		
Resin ID (ISO 1043)		PA6 + X GF30		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.41	--	g/cm ³	ISO 1183
Spiral Flow	70.0	--	cm	Internal Method
Molding Shrinkage				ISO 294-4
Across Flow	1.0	--	%	
Flow	0.40	--	%	
Humidity Absorption - 62% RH (70°C)	1.6	--	%	ISO 1110
Flexural Strain at Break ¹	3.2	--	%	ISO 178
Reinforcement Content	30	--	%	ISO 1172
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 961/30)	230	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10500	7500	MPa	ISO 527-2/1
Tensile Stress (Break)	170	115	MPa	ISO 527-2/5
Tensile Strain (Break)	2.6	4.2	%	ISO 527-2/5
Flexural Modulus ²	9600	--	MPa	ISO 178
Flexural Stress ³	250	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method

Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	10	kJ/m ²	
23°C	12	13	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	65	60	kJ/m ²	
23°C	70	70	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	205	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	160	--	°C	ISO 75-2/C
Melting Temperature ⁴	225	--	°C	DIN EN 11357-1
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate ⁵ (1.00 mm)	< 100	--	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB	--		UL 94
NOTE				
1.	2 mm/min			
2.	2.0 mm/min			
3.	2.0 mm/min			
4.	10 K/min, DSC			
5.	>1 mm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT