

Stanyl® TW341

Polyamide 46
DSM Engineering Plastics

Message:

Stanyl® TW341 is a Polyamide 46 (Nylon 46) material. It is available in Asia Pacific, Europe, or North America for injection molding.
Important attributes of Stanyl® TW341 are:
Flame Rated
Heat Stabilizer
Lubricated
Typical application of Stanyl® TW341: Automotive

General Information				
UL YellowCard		E43392-235049	E47960-240080	E172082-225894
Additive		Heat Stabilizer		
		Lubricant		
Features		Heat Stabilized		
		Lubricated		
Forms		Pellets		
Processing Method		Injection Molding		
Multi-Point Data		Isochronous Stress vs. Strain (ISO 11403-1)		
		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
		Shear Modulus vs. Temperature (ISO 11403-1)		
		Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.18	--	g/cm³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	2.0	--	%	
Flow	2.0	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	3.7	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2
--	3300	1000	MPa	
120°C	800	--	MPa	
160°C	650	--	MPa	
180°C	600	--	MPa	
200°C	500	--	MPa	
Tensile Stress				ISO 527-2

Yield	100	55.0	MPa	
Yield, 120°C	50.0	--	MPa	
Yield, 160°C	40.0	--	MPa	
Yield, 180°C	35.0	--	MPa	
Yield, 200°C	30.0	--	MPa	
Nominal Tensile Strain at Break				ISO 527-2
--	40	> 50	%	
120°C	> 50	--	%	
160°C	> 50	--	%	
180°C	> 50	--	%	
200°C	> 50	--	%	
Flexural Modulus				ISO 178
--	3000	900	MPa	
120°C	800	--	MPa	
160°C	600	--	MPa	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	4.0	4.0	kJ/m ²	
23°C	10	35	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Notched Izod Impact Strength				ISO 180/1A
-40°C	4.0	4.0	kJ/m ²	
23°C	10	35	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	190	--	°C	ISO 75-2/A
Melting Temperature ¹	295	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	8.5E-5	--	cm/cm/°C	
Transverse	1.1E-4	--	cm/cm/°C	
Thermal Index - 5000 hr	152	--	°C	IEC 60216
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+9	ohms · cm	IEC 60093
Electric Strength	25	15	kV/mm	IEC 60243-1
Comparative Tracking Index	400	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method

Flammability Classification			IEC 60695-11-10, -20
0.750 mm	V-2	--	
1.50 mm	V-2	--	
Injection	Dry	Unit	
Drying Temperature	80.0		°C
Drying Time	4.0 to 8.0		hr
Rear Temperature	280 to 320		°C
Middle Temperature	300 to 320		°C
Front Temperature	300 to 320		°C
Nozzle Temperature	300 to 320		°C
Processing (Melt) Temp	310 to 320		°C
Mold Temperature	80.0 to 120		°C
Injection Rate	Moderate-Fast		
Back Pressure	2.00 to 10.0		MPa
Screw Compression Ratio	2.5:1.0		
NOTE			

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

