

# Petrothene® NA594081

Low Density Polyethylene

LyondellBasell Industries

## Message:

Petrothene NA594081 is low molecular weight, low density polyethylene resin for wire and cable applications.

General Information		
Features	Low molecular weight	
	Low density	
Uses	Wire and cable applications	
Processing Method	Wire & Cable Extrusion	
Physical	Nominal Value	Unit
Density (23°C)	0.914	g/cm <sup>3</sup>
Melt Mass-Flow Rate (MFR)		
125°C/2.16 kg	10	g/10 min
190°C/2.16 kg	70	g/10 min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

