Eporex® 500

General Purpose Polystyrene

Eternal Plastics Co., Ltd.

Message:

Eporex[®] 500 is a General Purpose Polystyrene material. It is available in North America for injection molding. Important attributes of Eporex[®] 500 are: Flame Rated High Flow

| General Information | | | |
|--|-------------------|----------|-------------|
| Features | General Purpose | | |
| | High Flow | | |
| | | | |
| Uses | General Purpose | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.05 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) | 20 | g/10 min | ASTM D1238 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness (M-Scale) | 69 | | ASTM D785 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 41.0 | MPa | ASTM D638 |
| Tensile Elongation (Yield) | 2.0 | % | ASTM D638 |
| Flexural Modulus | 3140 | MPa | ASTM D790 |
| Flexural Strength (Yield) | 69.6 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (3.18 mm) | 16 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 | | | |
| MPa, Unannealed) | 75.0 | °C | ASTM D648 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | НВ | | UL 94 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

