

POLYFLAM® RIPP 4000 E

Polypropylene Copolymer

A. Schulman Europe

Message:

Unfilled flame-retardant PP-Copolymer, Extrusion grade, halogenfree

General Information			
Features	Copolymer		
	Workability, good		
	Halogen-free		
	Flame retardancy		
Processing Method	Extrusion		
	Injection molding		
Resin ID (ISO 1043)	PP FR(51)		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	2.00	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1600	MPa	ISO 527-2/1A/1
Tensile Stress			ISO 527-2/1A/50
Yield	15.0	MPa	ISO 527-2/1A/50
Fracture	12.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	3.7	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	100	%	ISO 527-2/1A/50
Flexural Modulus ¹	1600	MPa	ISO 178
Flexural Stress ²			ISO 178
4.4% strain	24.5	MPa	ISO 178
3.5% strain	24.2	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	3.0	kJ/m ²	ISO 179/1eA
23°C	7.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	35	kJ/m ²	ISO 179/1eU
23°C	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, not annealed	94.0	°C	ISO 75-2/B
1.8 MPa, not annealed	55.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	138	°C	ISO 306/A50
--	57.0	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.8 mm	V-0		IEC 60695-11-10, -20
1.6 mm	V-0		IEC 60695-11-10, -20
3.2 mm	V-0		IEC 60695-11-10, -20
Glow Wire Flammability Index			IEC 60695-2-12
0.75 mm	960	°C	IEC 60695-2-12
1.5 mm	960	°C	IEC 60695-2-12
3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
0.75 mm	700	°C	IEC 60695-2-13
1.5 mm	700	°C	IEC 60695-2-13
3.0 mm	700	°C	IEC 60695-2-13

Additional Information

- 1.)
Not for use in food contact applications2.)
Not for use in medical or pharmaceutical applications

Injection	Nominal Value	Unit
Drying Temperature	70	°C
Drying Time	2.0 - 4.0	hr
Processing (Melt) Temp	180 - 210	°C
Mold Temperature	40 - 80	°C
Injection Pressure	80.0 - 120	MPa
Injection Rate	Slow-Moderate	
Holding Pressure	40.0 - 90.0	MPa
Back Pressure	5.00 - 10.0	MPa
Screw Speed		mm/sec

Injection instructions

PredryingPredrying at 70°C for 2-4 hours is recommended as a precaution.ReprocessingAddition of regrind is normally possible, but it must be tested in each case regarding the percentage and requirements of the article. Thermal damage during first processing depends on processing parameters and the geometry of flow path and article.Shut downAvoid long melt residence time. Purge with base polymer or with polyolefines.FinishingMachining is usually possible.

NOTE	
1.	2.0 mm/min
2.	2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

