

Sarlink® TPE ML-1650N NAT (PRELIMINARY DATA)

Thermoplastic Elastomer
Teknor Apex Company

Message:

Sarlink ML-1600 series is a high performance, high flow thermoplastic elastomer series, available in NAT and BLK designed for automotive interior applications. Sarlink ML-1650N NAT is a medium hardness, medium density grade with excellent surface appearance suitable for injection molding.

General Information			
Features	Sunlight Resistant		
	Good formability		
	Good flexibility		
	Good tear strength		
	Good adhesion		
	Medium liquidity		
	Good chemical resistance		
	Good toughness		
	Fill		
	Excellent appearance		
	Elastic		
	Medium density		
	Medium hardness		
Uses	Washer		
	Application in Automobile Field		
	Car interior parts		
	Soft touch application		
	Soft handle		
	Rubber substitution		
	Knob		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.990	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	13	g/10 min	ASTM D1238

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ISO 868
Shore A, 1 second, injection molding	52		ISO 868
Shore A, 5 seconds, injection molding	50		ISO 868
Shore A, 15 seconds, injection molding	49		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹			ISO 37
Transverse flow: 100% strain	1.18	MPa	ISO 37
Flow: 100% strain	1.71	MPa	ISO 37
Tensile Stress ²			ISO 37
Transverse flow: Fracture	6.30	MPa	ISO 37
Flow: Fracture	5.00	MPa	ISO 37
Tensile Elongation ³			ISO 37
Transverse flow: Fracture	920	%	ISO 37
Flow: Fracture	780	%	ISO 37
Tear Strength ⁴			ISO 34-1
Transverse flow	19	kN/m	ISO 34-1
Flow	22	kN/m	ISO 34-1
Compression Set ⁵			ISO 815
23°C, 22 hr	20	%	ISO 815
70°C, 22 hr	37	%	ISO 815
90°C, 70 hr	63	%	ISO 815
125°C, 70 hr	92	%	ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁶			ISO 188
Transverse flow: 110°C, 1008 hr	13	%	ISO 188
Flow: 110°C, 1008 hr	11	%	ISO 188
Transverse flow: 100% strain 110°C, 1008 hr	3.5	%	ISO 188
Flow: 100% strain 110°C, 1008 hr	9.2	%	ISO 188
Transverse flow: 125°C, 168 hr	12	%	ISO 188
Flow: 125°C, 168 hr	12	%	ISO 188
Transverse flow: 100% strain 125°C, 168 hr	4.0	%	ISO 188
Flow: 100% strain 125°C, 168 hr	12	%	ISO 188
Change in Tensile Strain at Break in Air ⁷			ISO 188
Transverse flow: 110°C, 1008 hr	6.0	%	ISO 188
Flow: 110°C, 1008 hr	7.8	%	ISO 188
Transverse flow: 125°C, 168 hr	9.3	%	ISO 188
Flow: 125°C, 168 hr	9.3	%	ISO 188
Change in Shore Hardness in Air			
Shao A, 110°C, 1008 hr ⁸	3.6		ISO 188
Shao A, 110°C, 1008 hr ⁹	3.0		ISO 188

Shao A, 110°C, 1008 hr ¹⁰	2.7		ISO 188
Shao A, 125°C, 168 hr ¹¹	3.0		ISO 188
Shao A, 125°C, 168 hr ¹²	2.6		ISO 188
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 206 sec ⁻¹)	113	Pa·s	ASTM D3835

Legal statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Injection	Nominal Value	Unit
Rear Temperature	171 - 193	°C
Middle Temperature	177 - 199	°C
Front Temperature	182 - 204	°C
Nozzle Temperature	188 - 210	°C
Processing (Melt) Temp	188 - 210	°C
Mold Temperature	25 - 66	°C
Injection Pressure	1.38 - 6.89	MPa
Injection Rate	Moderate-Fast	
Back Pressure	0.172 - 0.345	MPa
Screw Speed	50 - 100	rpm
Cushion	3.81 - 25.4	mm

Injection instructions

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

NOTE

1.	Type 1, 510mm/min
2.	Type 1, 510mm/min
3.	Type 1, 510mm/min
4.	B method, right angle specimen (without cut), 510mm/min
5.	Type a
6.	Type 1
7.	Type 1
8.	15 sec
9.	5 sec
10.	1 sec
11.	15 sec
12.	5 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT