TPUCO® TPU-C95

Thermoplastic Polyurethane Elastomer (Polyester)

Taiwan PU Corporation

Message:

TPUCO® TPU-C95 is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) material. It is available in Asia Pacific for calendering. Primary attribute of TPUCO® TPU-C95: Wear Resistant.

Typical applications include:

Film

Sheet

| General Information | | | |
|------------------------------|---|------|-------------|
| Features | General Purpose Good Abrasion Resistance | | |
| | | | |
| | Good Wear Resistance | | |
| | | | |
| Uses | Film | | |
| | Sheet | | |
| | | | |
| Appearance | Clear/Transparent | | |
| Forms | Pellets | | |
| Processing Method | Calendering | | |
| Hardness | Nominal Value | | Test Method |
| Durometer Hardness (Shore A) | 95 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Abrasion Loss | 15.0 | mg | |
| Impact Resilience | 40 | % | |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress | | | ASTM D412 |
| 100% Strain | 7.85 | MPa | |
| 300% Strain | 11.8 | MPa | |
| Tensile Strength (Break) | 24.5 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 800 | % | ASTM D412 |
| Extrusion | Nominal Value | Unit | |
| Cylinder Zone 1 Temp. | 175 | °C | |
| Cylinder Zone 3 Temp. | 180 | °C | |
| Cylinder Zone 5 Temp. | 185 | °C | |
| Adapter Temperature | 190 | °C | |
| Die Temperature | 190 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

