

# Manner Flexible PVC 6926 NA 021

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

## Message:

Recommended Applications: 6926 is a UL QMTT2 Recognized Component product rated for THHW (as well as TW and THW) 75 °C wet and 105 °C dry insulation products. 6926 is stabilized without the use of lead products. 6926 is applicable for Style 1015 and MTW products, is rated for Oil Resistant I and II as well as VW-1 applications.

General Information			
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	Low (to None) Lead Content		
Uses	Automotive Applications		
	Wet Rated Insulation		
Agency Ratings	UL QMTT2		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38 to 1.42	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	42 to 48		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	19.0	MPa	ASTM D638
Tensile Elongation (Break)	300	%	ASTM D638
Additional Information	Nominal Value	Unit	
Stock Temperature - Recommended Extrusion	191	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT