

# VESTOLIT® E 7037

Polyvinyl Chloride  
VESTOLIT GmbH & Co. KG

Message:

VESTOLIT E 7037 is a low-emulsifier content, free-flwoing emulsion (E) PVC, which is used as a blending component with S- or M-PVC for the extrusion of rigid sections. In calendaring, it is used for producing semi-rigid and soft films when blended with S-PVC.

| General Information |                     |
|---------------------|---------------------|
| Features            | Good Flow           |
|                     | Good Processability |
| Uses                | Blending            |
|                     | Film                |
|                     | Piping              |
|                     | Profiles            |
| Forms               | Liquid              |
| Processing Method   | Calendering         |
|                     | Extrusion           |
|                     | Pipe Extrusion      |
|                     | Profile Extrusion   |

| Physical                   | Nominal Value | Unit              | Test Method |
|----------------------------|---------------|-------------------|-------------|
| Apparent Density           | 0.55          | g/cm <sup>3</sup> | ISO 60      |
| K-Value                    | 70.0          |                   | ISO 1628-2  |
| Sieve Analysis             |               |                   | ISO 4610    |
| -- <sup>1</sup>            | < 20          | %                 |             |
| -- <sup>2</sup>            | > 80          | %                 |             |
| Water Content <sup>3</sup> | < 0.30        | %                 | DIN 53715   |

| NOTE |                |
|------|----------------|
| 1.   | 0.2 mm sieve   |
| 2.   | 0.063 mm sieve |
| 3.   | Karl Fisher    |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

