ELASTICHEM[™] 6011TX-02

Flexible Polyvinyl Chloride

Colorite Polymers

Message:

ELASTICHEM[™] 6011TX-02 is a Flexible Polyvinyl Chloride product. It can be processed by extrusion or injection molding and is available in Asia Pacific, Europe, or North America. Applications of ELASTICHEM[™] 6011TX-02 include food contact applications and medical/healthcare. Characteristics include: Good Flexibility

Non-Toxic

| General Information | | | |
|------------------------------|---------------------------------|-------|-------------|
| Features | Good Flexibility | | |
| | Low Friction | | |
| | Low Gel | | |
| | Non-Toxic | | |
| | Resilient | | |
| | Tack Free | | |
| | | | |
| Uses | Medical/Healthcare Applications | | |
| Agency Ratings | FDA Unspecified Rating | | |
| Processing Method | Extrusion | | |
| | Injection Molding | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.18 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 60 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 3.36 | MPa | ASTM D638 |
| Tensile Strength | 13.3 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 470 | % | ASTM D638 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -54.0 | °C | ASTM D746 |
| Freezing Point | -45 | °C | ASTM D746 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

