# Sumikon® PM-725 (Type: JZ Black)

### Phenolic

**SBHPP** 

#### Message:

SUMIKON PM-725 Type JZ Black is a Graphite & Short Glass fiber molding compound based on Phenolic Novolac polymer. It is supplied in the form of Granular/Molding Powder for Molding.

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
	Graphite fiber reinforced material		
Appearance	Black		
Forms	Powder		
	Particles		
Processing Method Resin transfer molding			
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.69	g/cm³	JIS K6911
Molding Shrinkage - Flow	0.28	%	JIS K6911
Water Absorption (Equilibrium)	0.040	%	JIS K6911
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	107		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	48.0	MPa	JIS K6911
Flexural Strength	74.0	MPa	JIS K6911
Compressive Strength	146	MPa	JIS K6911
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.3	kJ/m²	JIS K6911
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8	4-0		
MPa, Unannealed)	173	°C	JIS K6911

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

