

ASTAMID™ MB3LW

Polyamide 6
Marplex Australia Pty. Ltd.

Message:

ASTAMID™ MB3LW is an Impact Modified, heat and UV stabilised Polyamide 6 (PA 6 or Nylon 6).
Note: The letters "U", "W" or "UV" indicate UV stabilisation has been added [ie: ASTAMID™ MB3LW].

General Information			
Additive	Impact modifier		
	heat stabilizer		
	UV stabilizer		
Features	Impact modification		
	Thermal Stability		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	20	g/10 min	ASTM D1238
Water Absorption (Equilibrium, 23°C, 50% RH)	2.5	%	

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (3.20 mm)	2750	MPa	ASTM D638
Tensile Strength ² (3.20 mm)	70.0	MPa	ASTM D638
Tensile Elongation ³ (Break, 3.20 mm)	5.0	%	ASTM D638
Flexural Modulus ⁴ (3.20 mm)	2350	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	170	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 3.20mm	150	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	65.0	°C	ASTM D648

Injection	Nominal Value	Unit
Drying Temperature	70.0 - 80.0	°C
Drying Time	2.0	hr
Rear Temperature	250 - 255	°C
Middle Temperature	255 - 265	°C
Front Temperature	265 - 270	°C
Processing (Melt) Temp	255 - 265	°C
Mold Temperature	50.0 - 80.0	°C
Injection Pressure	60.0 - 120	MPa

Injection Rate	Fast	
Back Pressure	0.100 - 0.500	MPa
Screw Speed	40 - 60	rpm
Clamp Tonnage	3.0 - 5.0	kN/cm ²

Injection instructions

Drying Time: > 12 hr for already open bag

NOTE

1.	5.0 mm/min
2.	5.0 mm/min
3.	5.0 mm/min
4.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT