

LubriOne™ PC-000/15T BL702

Polycarbonate
PolyOne Corporation

Message:
PTFE Filled, Lubricated Polycarbonate Compound

General Information			
Filler / Reinforcement	PTFE ultra fine powder		
Features	Lubrication		
Appearance	Blue		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Molding Shrinkage (3.00 mm)	0.50 - 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	55.0	MPa	ASTM D638
Tensile Elongation ² (Break)	20	%	ASTM D638
Flexural Modulus ³	2300	MPa	ASTM D790
Flexural Strength ⁴	80.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	250	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	130	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	110 - 130	°C	
Drying Time	4.0 - 6.0	hr	
Processing (Melt) Temp	280 - 310	°C	
Mold Temperature	80.0 - 120	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

