

# GAPEX® RPP20EB92BK

Polypropylene  
Ferro Corporation

Message:  
Please contact Ferro Corporation for additional information.

General Information		
Uses	Automotive Applications	
Forms	Pellets	
Injection	Nominal Value	Unit
Drying Temperature	71.1 to 82.2	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	221 to 238	°C
Middle Temperature	227 to 243	°C
Front Temperature	232 to 260	°C
Nozzle Temperature	232 to 260	°C
Processing (Melt) Temp	221 to 238	°C
Mold Temperature	37.8 to 65.6	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.138 to 0.345	MPa
Cushion	5.08 to 12.7	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT