

SHIN-A SE-70HEK75

Epoxy; Epoxide

SHIN-A T&C;

Message:

Biphenyl Epoxy

Biphenyl Novolac Epoxy

General Information		
Uses	Adhesives	
	Printed Circuit Boards	
Physical	Nominal Value	Unit
Viscosity ¹ (150°C)	< 1.00	Pa·s
Softening Point	74 to 76	°C
Epoxy Equivalent	280 to 300	g/eq
NOTE		
1.	ICI	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT