

CarmelStat™ CS 1115

Polypropylene
Carmel Olefins Ltd.

Message:
Elastomer modified PP for boxes, containers and pallets.

General Information			
Uses	Container		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.10	%	ASTM D955
Water Absorption (Equilibrium)	0.060	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	22.0	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1900	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	100	J/m	ASTM D256
Unnotched Izod Impact	230	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	150	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+9	ohms	ASTM D4496
Volume Resistivity	1.0E+9	ohms · cm	ASTM D257
Additional Information			

Volume Resistivity, ASTM D257: 1e6 to 1e9 ohm-cmSurface Resistivity, SEOS/ESD 11.11: 1e6 to 1e9 ohmsImpact Resistance, ASTM D5628: 11J

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT