

SureSpec LD20-020C

Low Density Polyethylene

Genesis Polymers

Message:

LD20-020C is a certified prime resin designed for high clarity Blown films for packaging of articles requiring good opticals. LD20-020C features optimal balance of film strength, stiffness, good openability and excellent sealability as well as easy processability. Maximum recommended film drawdown is 1.0 mil. LD20-020C contains medium slip and medium antiblock. LD20-020C complies with FDA regulation 21CFR 177.1520 (c) 2.2 and most international regulations concerning the use of Polyethylene in contact with food articles.

General Information			
Additive	Medium Antiblock		
	Medium Slip		
Features	Food Contact Acceptable		
	Good Processability		
	Good Stiffness		
	Good Strength		
	High Clarity		
	Low Density		
	Medium Antiblocking		
	Medium Slip		
	Opticals		
Uses	Blown Film		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520(c) 2.2		
Forms	Pellets		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	32	µm	ASTM D882
Secant Modulus			
1% Secant, MD : 32 µm	234	MPa	
1% Secant, TD : 32 µm	248	MPa	ASTM D882
Tensile Strength			
MD : Yield,32 µm	10.0	MPa	
TD : Yield,32 µm	11.0	MPa	

MD : Break, 32 μm	26.0	MPa	
TD : Break, 32 μm	15.0	MPa	
Tensile Elongation			ASTM D882
MD : Break, 32 μm	180	%	
TD : Break, 32 μm	550	%	
Dart Drop Impact ¹ (25 μm)	85	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 32 μm	370	g	
TD : 32 μm	160	g	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.0 μm, Blown Film)	75		ASTM D2457
Haze (25.0 μm, Blown Film)	5.5	%	ASTM D1003
NOTE			
1.	F50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

