Formolon® 186

Polyvinyl Chloride Alloy

Formosa Plastics Corporation, U.S.A.

Message:

F-186 is a medium molecular weight vinyl chloride/vinyl acetate copolymer, which exhibits good clarity and strength properties. Applications include extruded and calendered sheet as well as solution coatings.

| General Information | | | |
|-----------------------------|-------------------------|-------|-------------|
| Features | Good Strength | | |
| | Medium Clarity | | |
| | Medium Molecular Weight | | |
| | | | |
| Uses | Coating Applications | | |
| | Sheet | | |
| | | | |
| Agency Ratings | EC 1907/2006 (REACH) | | |
| Forms | Pellets | | |
| Processing Method | Calendering | | |
| | Solution Coating | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Apparent Density | 0.60 | g/cm³ | ASTM D1895A |
| K-Value ¹ (25°C) | 56.0 | | |
| Vinyl Acetate Content | 14.0 | wt% | |
| Inherent Viscosity | 0.69 | | ASTM D1243 |
| Relative Viscosity | 1.83 | | |
| Sieve Analysis ² | 99 | % | ASTM D1921 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

%

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

0.300

0.5 g/100 cc in Cyclohexanone

Through 40 Mesh Screen

Tel: +86 21 5895 8519

Volatiles

NOTE 1.

2.

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

