

Romiloy® 4010/07

Acrylonitrile Butadiene Styrene + Nylon

ROMIRA GmbH

Message:

Romiloy® 4010/07 is an acrylonitrile butadiene styrene nylon (ABS nylon) material. This product is available in Europe, and the processing method is injection molding.

Romiloy® The main features of 4010/07 are:

flame retardant/rated flame

High stiffness

Impact resistance

General Information			
Features	Rigidity, high		
	Impact resistance, high		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	30	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2000	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	43.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	100	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	1700	MPa	ISO 178
Flexural Stress ² (23°C)	66.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	19	kJ/m ²	ISO 179/1eA
23°C	72	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	107	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Additional Information			
Tensile Strain @ Break, DIN EN ISO 527, 50 mm/min, 23°C: >100%			
Injection	Nominal Value	Unit	
Drying Temperature	< 80.0	°C	
Drying Time	2.0 - 4.0	hr	

Suggested Max Moisture	0.050	%
Suggested Max Regrind	5	%
Rear Temperature	230 - 250	°C
Middle Temperature	230 - 250	°C
Front Temperature	230 - 250	°C
Processing (Melt) Temp	240 - 260	°C
Mold Temperature	50.0 - 90.0	°C
Injection Rate	Fast	
Back Pressure	1.00	MPa
Screw Speed	12 - 18	rpm

Injection instructions

Holding Pressure: moderate to high

NOTE

1. 2.0 mm/min
2. 2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT