

# BONDYRAM® 6000

Acrylonitrile Butadiene Styrene

Polyram Ram-On Industries

## Message:

Maleic Anhydride Modified ABS.

Compatibilizer and coupling agent for Styrene compounds.

General Information			
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm <sup>3</sup>	ISO 1183, ASTM D1505
Melt Mass-Flow Rate (MFR) (220°C/2.16 kg)	8.0	g/10 min	ASTM D1238, ISO 1133

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

