

Baoding 6126

Thermoplastic Polyurethane Elastomer

Baoding Bangtai Polymeric New-Materials Co.,Ltd

Message:

Properties: Hot melt adhsvie film. It can also used with MEK and EAC when dissolved. Also with high crystallization rate and especially has great bonding capacity with TPU, PVC, NYLON, and fabric.

Applications: Application: Fire hose, Shoe, Water seal, Ink print, Anti-explosion glass used into the high buildings.

General Information		
Features	Bondability	
	Good Adhesion	
Uses	Adhesives	
	Footwear	
	Hose	
	Printing Ink	
	Seals	
Appearance	White	
Physical	Nominal Value	Unit
Solution Viscosity ¹	1600 to 2200	mPa·s
Thermal	Nominal Value	Unit
Vicat Softening Temperature	45.0 to 55.0	°C
Additional Information	Nominal Value	Unit
Flow Beginning Temperature	80 to 90	°C
NOTE		
1.	15% solid content in MEK	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT