Stat-Tech™ NN-20CF/000 BK(EM00001819BJ)

Polyamide 66

PolyOne Corporation

Message:

Stat-Tech™ Electrically Conductive Compounds are specifically engineered to provide anti-static, ESD and RFI/EMI shielding performance for critical electronic equipment applications. These compounds combine the performance of select engineering resins with reinforcing additives such as carbon powder, carbon fiber, nickel-coated carbon fiber and stainless steel fiber, for low to high levels of conductivity depending upon application requirements.

| General Information | | | |
|----------------------------------|------------------------------------|-------|-------------|
| Features | Semicrystallization | | |
| | Rigidity, high | | |
| | Good chemical resistance | | |
| Uses | Computer components | | |
| | Electrical/Electronic Applications | | |
| | Aerospace applications | | |
| | Connector | | |
| | Business equipment | | |
| | Susmoss equipment | | |
| Forms | Particle | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.22 | g/cm³ | ISO 1183 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 15600 | МРа | ISO 527-2 |
| Tensile Stress | 215 | МРа | ISO 527-2 |
| Tensile Strain (Yield) | 1.0 - 2.0 | % | ISO 527-2 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength | 5.5 | kJ/m² | ISO 179 |
| Charpy Unnotched Impact Strength | 45 | kJ/m² | ISO 179 |
| Electrical | Nominal Value | Unit | Test Method |
| Surface Resistivity | 1.0E+2 - 1.0E+4 | ohms | IEC 60093 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

