

# THERMOLAST® K TC6HFZ (Series: UV/HF/SF)

Thermoplastic Elastomer

KRAIBURG TPE

## Message:

The UV/HF/SF Series is your material solution for applications requiring high UV resistance, perfect surface finish and high flow ability. It is particularly appropriate for automotive exterior components.

Typical applications

Cowls gaskets

Roof rims

Water deflectors

Window encapsulations

Material advantages

Easy flowing

Excellent processing behavior

Perfect adhesion to PP

Perfect surface finish

Tested according PV3930 for outdoor use

General Information			
Features	Good UV resistance		
	Workability, good		
	High liquidity		
	Excellent appearance		
Uses	Washer		
	Application in Automobile Field		
	Automotive exterior parts		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.03	g/cm <sup>3</sup>	ISO 1183
Spiral Flow	110	cm	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	60		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>1</sup> (Break)	5.00	MPa	ISO 37
Tensile Elongation <sup>2</sup> (Break)	550	%	ISO 37
Tear Strength <sup>3</sup>	14	kN/m	ISO 34-1
Injection	Nominal Value	Unit	
Drying Temperature	60 - 80	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	180	°C	
Middle Temperature	200	°C	

Front Temperature	220	°C
Mold Temperature	25 - 40	°C
Injection Pressure	20.0 - 100	MPa
Back Pressure	2.00 - 10.0	MPa

NOTE		
1.	Type S2, 200 mm/min	
2.	Type S2, 200 mm/min	
3.	Method B, right-angle specimen (cut)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT