Razalen® P111 GR30

Polypropylene Impact Copolymer Razin™ Engineering Plastics

Message:

Razalen P111 GR30 is an injection grade natural color impact copolymer polypropylene reinforced with 30% glass fiber. It combines good toughness rigidity balance.

General Information				
Filler / Reinforcement	Glass Fiber,30% Filler by Weight			
Additive	Impact Modifier			
Features	Good Impact Resistance			
	Good Toughness			
	Impact Copolymer			
	Impact Modified			
	Medium Rigidity			
Appearance	Natural Color			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.14	g/cm³	ASTM D792	
Melt Mass-Flow Rate (MFR) (230°C/2.16				
kg)	4.0	g/10 min	ASTM D1238	
Molding Shrinkage - Flow	0.30	<u>%</u>	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield)	70.0	MPa	ASTM D638	
Tensile Elongation (Break)	3.0	%	ASTM D638	
Flexural Modulus	5100	MPa	ASTM D790	
Flexural Strength	100	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (Area) (23°C)	14.0	kJ/m²	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
0.45 MPa, Unannealed	155	°C		
1.8 MPa, Unannealed	140	°C		
Injection	Nominal Value	Unit		
Drying Temperature	80.0 to 100	°C		
Drying Time	2.0 to 4.0	hr		
Rear Temperature	200 to 210	°C		
Middle Temperature	210 to 220	°C		
Front Temperature	220 to 230	°C		
Processing (Melt) Temp	220 to 240	°C		

Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	50.0 to 150	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

