

Halene P M340

Polypropylene Impact Copolymer

Haldia Petrochemicals Ltd.

Message:

M340 is a Heterophasic Polypropylene Impact Copolymer (PPiCP), produced by the latest generation Spheripol II Technology. This PPiCP is primarily suitable for Injection Molding & Compounding process.
M340 combines excellent processability with high Flow, low Cycle Time, excellent Impact - Stiffness balance, Low Warpage and good Gloss.

General Information			
Features	Fast Molding Cycle		
	Good Impact Resistance		
	Good Processability		
	Good Stiffness		
	High Flow		
	Impact Copolymer		
	Low Warpage		
	Medium Gloss		
Uses	Appliance Components		
	Automotive Applications		
	Compounding		
	Containers		
	Food Containers		
	Furniture		
	Household Goods		
	Industrial Applications		
	Thin-walled Containers		
Forms	Pellets		
Processing Method	Compounding		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density ¹	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	40	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Injection Molded)	24.0	MPa	ASTM D638
Tensile Elongation (Yield, Injection Molded)	5.0	%	ASTM D638
Flexural Modulus (Injection Molded)	1200	MPa	ASTM D790A

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	60	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	88.0	°C	ASTM D648
Vicat Softening Temperature	140	°C	ASTM D1525 ²
Injection	Nominal Value	Unit	
Rear Temperature	160 to 250	°C	
Middle Temperature	160 to 250	°C	
Front Temperature	160 to 250	°C	
Mold Temperature	30.0 to 40.0	°C	
NOTE			
1.	23°C		
2.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

