

DISTRUMID 6 MV

Polyamide 6

Distrupol

Message:

DISTRUMID 6 MV is a polyamide 6 (nylon 6) material. This product is available in Europe. The main characteristics of DISTRUMID 6 MV are: flame retardant/rated flame.

General Information				
Forms		Particle		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.14	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.1	--	%	ASTM D955
Water Absorption (24 hr)	1.4	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	120	104		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength (Yield)	80.0	40.0	MPa	ASTM D638
Tensile Elongation (Break)	220	270	%	ASTM D638
Flexural Modulus	2800	900	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact	50	800	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, not annealed	180	--	°C	ASTM D648
1.8 MPa, not annealed	75.0	--	°C	ASTM D648
Vicat Softening Temperature	205	--	°C	ASTM D1525
Melting Temperature	222	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+11	ohms	ASTM D257
Volume Resistivity	1.0E+15	1.0E+11	ohms·cm	ASTM D257
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating	V-2	--		UL 94
Additional Information				

干燥

Continuous Service Temperature, S.P., No Stress: 80 °CResistance to Tracking, VDE 0303/1: KC>450 V

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

