

SLOVALEN® PC 78 FRD 1

Polypropylene

Plastcom

Message:

Modified copolymer PP with the possibility of changing the ITT-index within the interval 5 - 20 g/10 min. Stabilized against the UV radiation and atmospheric conditions by the UV stabilizer on the HALS basis. Retarded with the halogen flame retardant. Application - stadium seats with guaranteed life-cycle of the mechanical and surface properties, electrical industry - terminals, coil forms, covers of electrotools, guides. Fulfills 960°C glow wire and flammability in accordance with UL 94 V2. Concerning flammability, it complies with the building norm DIN 4102- B2. Delivered in the full RAL colour scale.

General Information			
Additive	Flame Retardant		
Features	Copolymer		
	Flame Retardant		
	Halogenated		
Uses	Electrical/Electronic Applications		
	Power/Other Tools		
	Seats		
Appearance	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PP		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	2.4	%	
Flow	2.4	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1300	MPa	ISO 527-2
Tensile Stress (Yield)	28.0	MPa	ISO 527-2
Tensile Strain (Yield)	20	%	ISO 527-2
Flexural Modulus	1100	MPa	ISO 178
Flexural Stress	40.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	5.0	kJ/m ²	
23°C	10	kJ/m ²	

Charpy Unnotched Impact Strength			ISO 179
-20°C	110	kJ/m²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	75.0	°C	ISO 75-2/B
Vicat Softening Temperature	110	°C	ISO 306/B
Melting Temperature (DSC)	150	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Electric Strength	24	kV/mm	IEC 60243-1
Comparative Tracking Index (Solution A)	450	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94
Glow Wire Ignition Temperature	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 to 250	°C	
Mold Temperature	30.0 to 50.0	°C	
Injection Pressure	50.0 to 80.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT