SEETEC LDPE XL505

Low Density Polyethylene

Lotte Chemical Corporation

Message:

SEETEC XL505 resin is produced by ExxonMobil Chemical's autoclave process technology. SEETEC XL505 resin is an excellent raw material in the application of extrusion coating.

General Information			
Uses	Coating Applications		
	Laminates		
RoHS Compliance	RoHS Compliant		
Processing Method	Extrusion Coating		
Physical	Nominal Value	Unit	Test Method
Density	0.916	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Oxygen Permeability	220	cm ³ ·mm/m ² /atm/24 hr	ASTM D3985
Water Vapor Transmission Rate (38°C, 90 RH, 25 μm)	% 18	g/m²/24 hr	ASTM F372
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	87.0	°C	ASTM D1525
Melting Temperature	105	°C	Internal Method
Extrusion	Nominal Value	Unit	Test Method
Minimum Coating Weight ¹ (315°C)	16	g/m²	Internal Method
Neck-in ² (315°C)	29.0	mm	Internal Method
NOTE			
1.	Constant Output		
2.	Constant Output, 50 m/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

