

CONTINUUM™ DGDA-2502 NT

Bimodal Polyethylene Resin

The Dow Chemical Company

Message:

CONTINUUM™ DGDA-2502 NT Bimodal Polyethylene Resin is produced using UNIPOL™ II process technology. This product may be utilized for pipe applications where long-term hydrostatic strength combined with outstanding resistance to slow crack growth, rapid crack propagation, and high melt strength is desired. Suitable applications include natural gas distribution pipes, large diameter industrial piping, mining, sewage, and municipal water service lines. DGDA-2502 NT has excellent processability for the full range of pipes sizes and wall thicknesses to include heavy wall pipe.

Industrial Standards Compliance:

ASTM D 3350: cell classification

Natural - PE445574A

Black - PE445574C (see Notes 1 & 2)

Plastics Pipe Institute (PPI): TR-4

Natural Pipe - CONTINUUM™ DGDA-2502 NT

ASTM PE4710 pipe grade - 1600psi HDB, 1000psi HDS @ 73oF, and 1000psi HDB @ 140oF

Black Pipe - CONTINUUM DGDA-2502 BK (see Notes 1 & 2)

ASTM PE4710 pipe grade - 1600psi HDB, 1000psi HDS @ 73oF, and 1000psi HDB @ 140oF

NSF International : Standard 14 & 61

Natural Pipe - DGDA-2502 NT

Black Pipe - DGDA-2502 BK (see Notes 1 & 2)

Consult the regulations for complete details.

Notes:

(1) The first five numbers of the cell classification are based on natural resin. The last number and letter are based on black resin (natural resin plus 6.5% DFNF-0092).

(2) Natural resin extruded under proper conditions with carbon black masterbatch DFNF-0092 (6.5%).

General Information			
Additive	Processing Aid		
Forms	Pellets		
Processing Method	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Density			ASTM D1505
Natural	0.949	g/cm ³	
Black ¹	0.959	g/cm ³	
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	0.040	g/10 min	
190°C/21.6 kg	12	g/10 min	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	61		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	> 24.1	MPa	
Break	> 32.1	MPa	
Tensile Elongation			ASTM D638
Yield	> 16	%	
Break	> 500	%	
Flexural Modulus ²	924	MPa	ASTM D790B

Resistance to Rapid Crack Propagation, Pc - S-4 ³ (0°C)	> 12.0	bar	ISO 13477
Resistance to Rapid Crack Propagation, Tc - S-4 (5 bar) ⁴	-1	°C	ISO 13477
Slow Crack Growth PENT - 2.4 MPa (80°C)	> 10000	hr	ASTM F1473
Thermal Stability	> 220	°C	ASTM D3350
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	72.8	°C	ASTM D648
Brittleness Temperature	< -75.0	°C	ASTM D746A
Vicat Softening Temperature	127	°C	ASTM D1525
Melting Temperature (DSC)	113	°C	Internal Method
NOTE			

1.

Natural resin extruded under proper conditions with carbon black masterbatch DFNF-0092 (6.5%).

2.

Method I (3 point load)

3.

Pipe diameter of 10 inch IPS (25.4 cm) and Standard Diameter Ratio (SDR) 11.

4.

Pipe diameter of 10 inch IPS (25.4 cm) and Standard Diameter Ratio (SDR) 11.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT