

NORYL™ WCV063 resin

Polyphenylene Ether + SEBS + Polyolefin

SABIC Innovative Plastics

Message:

Flexible, non-halogenated FR, mPPE extrusion grade material for evaluation in automotive wire coating applications requiring ISO6722.

General Information			
Features	Good flexibility Halogen-free Flame retardancy		
Uses	Wire and cable applications Wire sheath Application in Automobile Field		
Agency Ratings	ISO 6722		
Processing Method	Extrusion coating		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (280°C/5.0 kg)	33	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	63		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	840	MPa	ASTM D638
--	690	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	28.0	MPa	ASTM D638
Yield	25.0	MPa	ISO 527-2
Fracture ³	28.0	MPa	ASTM D638
Fracture	25.0	MPa	ISO 527-2/50
Tensile Strain			
Yield	20	%	ISO 527-2/50
Fracture ⁴	90	%	ASTM D638
Fracture	50	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁵	720	MPa	ASTM D790
--	790	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			

-30°C	170	J/m	ASTM D256
23°C	560	J/m	ASTM D256
-30°C ⁶	14	kJ/m ²	ISO 180/1A
23°C ⁷	37	kJ/m ²	ISO 180/1A

Thermal	Nominal Value	Unit	Test Method
---------	---------------	------	-------------

Deflection Temperature Under Load

0.45 MPa, unannealed, 3.20mm	82.0	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	56.0	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁸	66.0	°C	ISO 75-2/Af

Electrical	Nominal Value	Test Method
------------	---------------	-------------

Dielectric Constant (1.00 GHz)	2.47	ASTM D150
Dissipation Factor (1.00 GHz)	3.2E-3	ASTM D150

Extrusion	Nominal Value	Unit
-----------	---------------	------

Drying Temperature	80.0 - 100	°C
Drying Time	4.0 - 6.0	hr
Suggested Max Moisture	0.020	%
Cylinder Zone 1 Temp.	200 - 260	°C
Cylinder Zone 3 Temp.	270 - 300	°C
Cylinder Zone 5 Temp.	280 - 300	°C
Melt Temperature	280 - 300	°C
Die Temperature	280 - 300	°C

Extrusion instructions

Compression Ratio 2;1-3:1 Conductor Pre-heat Temperature: 100 - 150 °C Cooling Water Air Gap: 100 - 1000 mm Cross-head Temperature: 280 - 300 °C Drying Time (Cumulative): 8 hrs Extruder Length/Diameter Ratio (L/D): >24:1 Neck Temperature: 280 - 300 °C Screen Pack: 60/200/60 Screw Speed: 5 - 60 rpm Water Bath Temperature: 15 - 30 °C

NOTE

1.	50 mm/min
2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	Type 1, 50mm/min
5.	1.3 mm/min
6.	80*10*4
7.	80*10*4
8.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

