

# Innothane® FM-2080

Polyurethane Thermoset Elastomer

Innovative Polymers, Inc.

Message:

FM-2080 is a rigid polyurethane foam formulated for hand-batch and meter-mix dispensing methods. Excellent physical properties can be obtained with a room temperature cure without the utilization of mercury, MOCA, or TDI.

General Information		
Features	High Rigidity	
Uses	Foam	
RoHS Compliance	RoHS Compliant	
Appearance	Tan	
Physical	Nominal Value	Unit
Specific Gravity		
Cured	0.128 to 0.176	g/cm <sup>3</sup>
Hardener	1.16	g/cm <sup>3</sup>
Base Resin	1.20	g/cm <sup>3</sup>
Thermoset	Nominal Value	Unit
Thermoset Components		
	Mix Ratio by Volume: 100	
Hardener	Mix Ratio by Weight: 97	
	Mix Ratio by Weight: 100	
Resin	Mix Ratio by Volume: 100	
Demold Time	10 to 20	min
Cream Time	35.0 to 45.0	sec
Rise Time	1.3 to 1.7	min
Uncured Properties	Nominal Value	Unit
Viscosity		
25°C <sup>1</sup>	0.10	Pa · s
25°C <sup>2</sup>	0.25	Pa · s
25°C <sup>3</sup>	0.68	Pa · s
Curing Time (25°C)	1.7E+2	hr
NOTE		
1.	Resin	
2.	Mixed	
3.	Hardener	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

