# POLYPRO® 5014

### Polypropylene Homopolymer

YUHWA Korea Petrochemical Ind. Co., Ltd.

#### Message:

POLYPRO® 5014 is a Polypropylene Homopolymer (PP Homopolymer) material. It is available in Asia Pacific. Primary attribute of POLYPRO® 5014: Homopolymer. Typical applications include: Adhesives/Tapes Food Contact Applications Straps/Ropes Yarn

General Information			
Features	General Purpose		
	Homopolymer		
Uses	Netting		
	Rope		
	Таре		
	Yarn		
Agency Ratings	FDA Food Contact, Unspecified Rat	ting	
Forms	Pellets	- J	
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	3.2	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.0 to 2.0	%	Internal Method
Water Absorption (Equilibrium)	< 0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	96		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	35.3	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1470	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	39	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	105	°C	ASTM D648
Vicat Softening Temperature	152	°C	ASTM D1525
Peak Melting Temperature	162	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

