

KOPA® KN135G33BLHS

Polyamide 6

Kolon Plastics, Inc.

Message:

KOPA® KN135G33BLHS is a Polyamide 6 (Nylon 6) product filled with 33% glass fiber. It is available in Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

Good Dimensional Stability

Good Weather Resistance

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Features	Good Dimensional Stability Good Weather Resistance		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.40	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	167	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	7.5	%	ASTM D638
Flexural Modulus (23°C)	8700	MPa	ASTM D790
Flexural Strength (23°C)	265	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	170	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	210	°C	
1.8 MPa, Unannealed	205	°C	
Peak Melting Temperature	220	°C	ASTM D1525
CLTE - Flow	3.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.60		ASTM D150
Arc Resistance	130	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

