

Mirathane™ L95

Thermoplastic Polyurethane Elastomer (Polycaprolactone)

Miracll Chemicals Co., Ltd.

Message:

Mirathane™ L95 is a Thermoplastic Polyurethane Elastomer (Polycaprolactone) (TPU-Capro) product. It is available in Asia Pacific. Applications of Mirathane™ L95 include engineering/industrial parts, film, sealing applications and sheet.

General Information			
Uses	Film		
	Gaskets		
	Seals		
	Sheet		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	95		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance	20.0	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	14.0	MPa	
300% Strain	25.0	MPa	
Tensile Strength (Yield)	40.0	MPa	ASTM D412
Tensile Elongation (Break)	370	%	ASTM D412
Tear Strength	145	kN/m	ASTM D624
Compression Set			ASTM D395
23°C, 72 hr	30	%	
70°C, 22 hr	45	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ¹	-35.0	°C	ASTM D3417
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

