

NORYL™ FXN4020H resin

Polyphenylene Ether + PS

SABIC Innovative Plastics

Message:

high gloss NORYL

General Information			
UL YellowCard	E207780-100148376		
Features	Highlight		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/5.0 kg)	25	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (280°C/2.16 kg)	25.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.060	%	ISO 62
Equilibrium, 23°C, 50% RH	9.0E-3	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2560	MPa	ASTM D638
--	2500	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	67.0	MPa	ASTM D638
Yield	58.0	MPa	ISO 527-2/50
Fracture ³	55.0	MPa	ASTM D638
Fracture	46.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	3.6	%	ASTM D638
Yield	3.3	%	ISO 527-2/50
Fracture ⁵	5.2	%	ASTM D638
Fracture	4.4	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2730	MPa	ASTM D790
-- ⁷	2500	MPa	ISO 178
Flexural Stress			
--	85.0	MPa	ISO 178
Yield, 50.0mm span ⁸	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength ⁹ (23°C)	10	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	20	J/m	ASTM D256
23°C	85	J/m	ASTM D256
-30°C ¹⁰	4.6	kJ/m ²	ISO 180/1A
23°C ¹¹	8.0	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	30.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	75.0	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	83.0	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	75.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	96.0	°C	ASTM D1525, ISO 306/B50 ¹¹ ¹³
--	98.0	°C	ISO 306/B120
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	7.7E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	7.9E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Flammability	Nominal Value	Test Method	
Flame Rating			UL 94
1.50 mm, Testing by SABIC	V-1		UL 94
2.50 mm, Testing by SABIC	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	76.7 - 82.2	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	30 - 70	%	
Rear Temperature	216 - 266	°C	
Middle Temperature	227 - 271	°C	
Front Temperature	238 - 277	°C	
Nozzle Temperature	249 - 277	°C	
Processing (Melt) Temp	249 - 277	°C	
Mold Temperature	54.4 - 76.7	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	20 - 100	rpm	
Vent Depth	0.038 - 0.051	mm	
NOTE			
1.	5.0 mm/min		
2.	Type 1, 50mm/min		
3.	Type 1, 50mm/min		

4.	Type 1, 50mm/min
5.	Type 1, 50mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

